



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A22C 13/00	A1	(11) International Publication Number: WO 93/12660 (43) International Publication Date: 8 July 1993 (08.07.93)
(21) International Application Number: PCT/GB92/02381 (22) International Filing Date: 23 December 1992 (23.12.92) (30) Priority data: 9127463.9 28 December 1991 (28.12.91) GB (71) Applicant (for all designated States except US): DEVRO LIMITED [GB/GB]; Moodiesburn, Chryston, Glasgow G69 0JE (GB). (72) Inventors; and (75) Inventors/Applicants (for US only) : MORGAN, Trevor, Francis [GB/GB]; 11 Friars Way, Airdrie ML6 9QW (GB). FRAME, Gordon [GB/US]; 417 Conover Drive, Hillsborough TWP., Neshanic, NJ 08853 (US). KOBUSSEN, Petrus, Johannes [NL/NL]; Logtenburg 1, NL-5465 La Veghel (NL).		(74) Agents: McCALLUM, William, Potter et al.; Cruikshank & Fairweather, 19 Royal Exchange Sq., Glasgow G1 3AE (GB). (81) Designated States: AT, AU, BB, BG, BR, CA, CH, CS, DE, DK, ES, FI, GB, HU, JP, KP, KR, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, UA, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: CO-EXTRUDED COLLAGEN COATED FOODSTUFFS (57) Abstract <p>Sausages are produced by co-extruding a uniform layer of acid collagen gel around an extruded edible meat product, and chemically coagulating the co-extruded gel in a bath containing a chemical coagulating agent, such as to provide a collagen casing of sufficient mechanical strength to allow mechanical formation of sausage links by twist-linking or crimping. Preferably a coagulating agent such as liquid smoke is included in the collagen gel prior to extrusion. The coagulating bath may comprise a dehydrating agent such as alkali or a salt solution. No expensive air drying step is required in order to produce continuous casings of good strength.</p>		

details

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

- 1 -

CO-EXTRUDED COLLAGEN COATED FOODSTUFFS

The invention relates to a process and apparatus for the production of co-extruded collagen coated foodstuffs such as sausages.

While the process relates particularly to the production of sausages, it may also be used in the production of other collagen coated foodstuffs such as fish or meat products or products containing vegetable or cheese or both. Thus, while the description of the process will be in terms of the production of strings of sausages, the process is clearly not limited to that particular foodstuff.

There are known processes of co-extruding sausages or sausage-like materials. One particular process is disclosed in patent specification GB1232801. Essentially, the process involves extruding a cylindrical core of sausage meat mix and simultaneously extruding around the sausage meat an outer casing of a collagen gel. The collagen gel has a high water content and the gel is coagulated by removal of some of the water by osmosis by passage through a concentrated sodium chloride bath. However, coagulation of the collagen casing is not complete at this stage so that the casing is relatively weak in terms of mechanical properties. In particular, there would not generally be sufficient strength to enable crimping or twist linking to take place. In the conventional process, the co-extruded sausage is then cut

- 2 -

into individual sausages which are transported to a hot air drying cabinet where the hardening of the casing is completed and at the same time some partial cooking of the sausage meat occurs.

This process is thus not suitable for the production of twist link sausages. At the end of the brine bath, the collagen casing has insufficient strength to allow twist linking to be successfully carried out. On the other hand, after completion of hardening of the casing, partial cooking of the sausage meat has occurred. A partially cooked sausage is unsuitable for twist linking, due to solidification of the sausage meat.

A further disadvantage of the conventional process is that the air drying stage is costly in terms of energy consumption.

Japanese patent application 63-219473 (publication H2-69139) suggests the addition of a liquid smoke solution into the collagen gel immediately prior to co-extrusion in order to overcome problems of splitting of the sausage casing during the air drying stage.

It is an object of the present invention to mitigate these problems and provide a process which avoids the costly air drying stage, and also allows the production of twist linked strings of sausages.

- 3 -

The present invention provides a process of producing co-extruded sausage which comprises:

- co-extruding a substantially uniform layer of collagen gel around an extruded edible product; and
- chemically coagulating the co-extruded collagen gel using a chemical coagulating agent in the absence of heated air drying, such as to provide around the edible product a coagulated collagen casing of sufficient strength to allow mechanical separation into sausage links.

The invention also provides a corresponding apparatus for carrying out the process; and to the product itself.

The term "coagulating" is a term of art in the production of collagen coated sausage material and is not strictly scientific in the sense in which it is used. Coagulating as used in this specification refers to the step involving hardening and stabilisation of the casing. This is principally achieved in two ways; firstly by removal of water from the collagen gel, and secondly by cross-linking the collagen. Either or both of these methods may be employed as appropriate.

Thus, it is known that collagen is a protein able to form aqueous gels of high water content. Typically, maximum gel water uptakes can be achieved at a pH of around 2 and a pH of around 13 which correspond roughly to the points of maximum swelling of the collagen protein. Higher water uptakes are generally found in the acid

- 4 -

region and for this reason acid collagen gels are often used for extrusion purposes. Thus, coagulation of the collagen can be brought about by water removal from the gel, for example by the use of concentrated salt solutions (such as sodium chloride) which remove water by osmosis, or by the use of a solution which changes the pH of the collagen gel such that water is lost from the gel. Thus, one embodiment of the present invention, envisages the use of an acidic gel and an alkaline coagulation agent which neutralises the acid and leads to water loss in the gel (for example, a solution of sodium hydroxide, sodium carbonate, ammonium sulphate, sodium bicarbonate, or ammonium hydroxide; or even by means of gaseous ammonia).

Alternatively or additionally, coagulation may be brought about by means of chemical modification of the collagen, such as by cross-linking. Suitable chemical modification systems include the use of glutaraldehyde, glyoxal, liquid smoke, sugars and mineral tanning agents. Liquid smoke is a well known material in the art and is for example described in patent GB1432271. Modification of the collagen casing may be brought about by proteolysis, caramel addition, or by the use of modified polysaccharides, for example propylene glycol alginate or hydroxy propyl methyl cellulose. Cellulose fiber may also be added for certain cooking properties.

Certain chemical modifying agents are suitable for inclusion in the gel prior to extrusion, particularly

- 5 -

cross-linking agents such as glutaraldehyde, and liquid smoke. Vegetable oil may be included in the gel to control coagulation and surface characteristics (such as clarity and permeability). According to a preferred embodiment of the invention, a coagulating agent which is a cross-linking agent (such as glutaraldehyde, glyoxal, liquid smoke, sugars and mineral tanning agents) is included in the collagen gel prior to extrusion, and the co-extruded collagen casing is then subject to coagulation by water loss in the post extrusion bath. This enables a coagulated collagen casing of sufficient strength to be produced, which may be twist-linked, crimped or otherwise mechanically separated into sausage links without breakage or disintegration.

The preferred chemical coagulating bath has a pH in the range 8 to 12, and preferably 9 to 10; and a temperature of 5 to 45°C, preferably 35 to 40°C.

The process is much less costly than the standard processes because it omits the expensive and time consuming mechanical drying. Air drying is the most usual form of drying employed in conventional co-extrusion processes and it is the main feature which limits the speed of the process. Thus, the present invention not only produces a product which can be directly handled and/or hung but one which is much cheaper to operate than known co-extrusion processes.

Preferably, the collagen gel is an acidic gel at a pH

- 6 -

of 1 to 4. Usually, the gel comprises 90 to 95% water. The collagen gel may be cooled to a temperature of 4 to 16°C prior to extrusion.

A preferred collagen gel comprises 4 to 10% collagen, 0.1 to 2% cellulose, 0.05% to 0.5% hydrochloric acid, preferably 0.3%, the balance being water.

Colouring agents may be included in the casing, for example by incorporating a colouring agent in the gel itself, or within a crosslinking agent (such as liquid smoke) injected into the gel prior to extrusion. Alternatively, the colouring agent may be injected independently into the gel prior to extrusion thereof.

The co-extruded edible product may also be coloured if desired, depending on the desired appearance characteristics.

Suitable colouring agents are well known in the art and include, for example, annato, sunset yellow, curcumin, cochineal, tartrazine yellow etc.

Usually, the amount of collagen gel co-extruded around the edible product is 3 to 10% of the total weight of gel and edible product. Preferably, the finished coagulated collagen gel casing has a thickness of 10 to 30 microns. The thickness is generally in proportion to the diameter of the sausage.

Usually, a coagulation time of 5 to 300 seconds is employed in order to allow coagulation to be substantially completed. This is preferably achieved by passing the

- 7 -

co-extruded product from the coagulation baths into a holding chamber, such as a spiral trough or flume downstream with the coagulating bath to allow substantial completion of coagulation. Further coagulating solution or other treatment solutions may be passed concurrently down the flume or showered thereinto. The co-extruded product is then preferably washed prior to separation into linking.

In a modification of the process, after the chemical coagulating bath, the product was subjected to chemical dehydration employing a chemical dehydrating agent, such as sodium carboxymethyl cellulose, 0.1 to 2% solution and preferably 1% solution.

The process according to the present invention allows the continuous non-batch production of linked sausages, which has not been possible hitherto. Thus, conventional link sausages are produced in batch mode using discrete lengths of preformed natural or reconstituted collagen casings placed on a stuffing horn. The conventional arrangement does not allow the production of continuous lengths of linked sausage. Thus, the present invention is well suited to industrial production and packaging techniques.

An embodiment of the invention will now be described by way of example only in conjunction with Figure 1 which is a schematic flow chart of a process and apparatus according to the invention.

- 8 -

A sausage meat paste mix is delivered from a vacuum filler 2 (e.g. a Handtmann FA30 or PA30) by a meat metering pump 4 to a co-extruder 6. An acid collagen gel is delivered from a gel storage vessel 8 by means of a gel metering pump 10. The gel storage vessel is usually pressurised to assist delivery of the gel, which has been prepared from hide splits, homogenised and filtered according to known technology.

Liquid smoke (or other cross-linking agent) from a container 12 is metered by a metering pump 14 into the collagen gel prior to co-extrusion. X

The co-extruder may be of a design known in the art such as a conical extruder or a contra-rotating disc extruder such as disclosed in patent specification US 3122788. The co-extruder extrudes a core of sausage meat through a central round die, and extrudes simultaneously a coating of collagen gel onto the meat core via an annular die surrounding the central round die.

The co-extruded coated sausage meat passes into a coagulation treatment bath 16 which comprises a shallow stainless steel trough having therein a conveyor formed of wire links to enable coagulation solution to freely contact the co-extruded collagen coating. Typically the trough is 2 to 10 m long in order to provide the desired residence time. Part of the coagulation solution is bled off and replaced by fresh solution from a feed stock tank 18 supplied from a make-up tank 20 in order to maintain

correct concentrations in the solution.

In order to allow coagulation to be completed the co-extruded sausage is then passed into a spiral solution trough 22. The trough 22 is a spiral or a helical flume (length 10 to 50 m) in order to provide the desired residence time in a compact arrangement. Usually the co-extruded sausage is fed into an upper end and passes down by gravity. A haul-off (not shown) may be provided at the downstream end. As required, further coagulating solution and/or washing solution may be passed down the flume (or showered onto the sausage) in order to complete the treatment.

At this stage the coagulated collagen sausage casing has a strength which is substantially its finished strength and is adequate to allow conventional twist-linking or crimping in linker 24. The collagen casing is strong enough to be twisted or crimped. Equally, the co-extruded sausage may be cut into individual sausages at this point if desired. The sausage meat paste inside is, however, still fluid enough to be displaced during the twisting or crimping operation (in contrast to the conventional process where full strength in the casing is only achieved after air drying and partial cooking and solidification of the sausage meat paste).

The twist-linked or crimped sausage string may then be hung and smoked in cabinet 26 according to conventional practice.

EXAMPLES

The following Examples illustrate the invention and were carried out by extrusion of a central core of sausage meat mixture typically of pH5 at about 4°C, and co-extrusion of a collagen gel through an annular die around the central core. The collagen gel was typically an acid gel of pH2 to 3 at a temperature of about 6°C. The co-extruded product was usually led into a sodium carbonate coagulation bath which typically increased the pH of the collagen gel casing to around pH10 to 11 thereby dewatering the gel. The tensile strengths were measured after substantial completion of coagulation of the collagen casing. Any liquid smoke was metered into the gel upstream of the co-extruder head.

EXAMPLE 1 (Varying Coagulation Time)

The experimental conditions were as follows:

extrusion speed	= 9.75 m/minute
gel type	= 4.7% collagen, 5.8% solids
gel quantity	= 170 g/minute
extrusion calibre	= 16mm
coagulation solution	= 16.7% w/w aqueous sodium carbonate at 18°C.

The results are given in Table 1. Tensile strengths of at least 1.0kg would generally be required to produce an acceptable product. The bursting calibre is obtained by squeezing the sausage meat up and so expanding the casing until it bursts.

- 11 -

TABLE 1

Contact Time with Coagulation Solution	Bursting calibre (mm)	Tensile Strength (kg) (Extrusion Direction)
---	--------------------------	--

16 sec	20-22	0.323
26 sec	20-21	0.273
46 sec	21	0.312

EXAMPLE 2 (sodium carbonate and glutaraldehyde coagulating agents)

The experimental conditions were as follows:

extrusion speed	=	9.14m/minute
gel type	=	4.7% collagen, 5.8% solids
gel flow rate	=	200g/minute
extrusion calibre	=	18-19mm

The results are given in Table 2.

TABLE 2

Solution Type	Contact Time of Solution (sec)	Tensile Strength (kg) (extrusion direction)
22% w/w Na ₂ CO ₃	16	0.616
at 35°C	26	0.681
	36	0.887
22% w/w Na ₂ CO ₃ +		
500ppm Glutaraldehyde	16	0.888
at 35°C	26	1.130
	36	1.215

- 12 -

EXAMPLE 3 (liquid smoke in collagen gel)

The experimental conditions were as follows:

extrusion speed = 9.14 m/min
gel type = 4.7% collagen, 5.3% solids
extrusion calibre = 26mm
coagulation solution = 21% w/w sodium carbonate @ 33-44°C
contact time with solution = 40 seconds.

Liquid smoke was injected directly into the gel stream upstream of the co-extruder.

The results are given in Table 3.

TABLE 3

Smoke type	Smoke level	Bursting	Tensile Strength kg
	(% of gel volume)	calibre mm	(Extrusion direction)
Zesti 10DC	10	29-31	1.15
Imperial 400N	10	30-31	1.08
Zesti 10DC	5	29-30	1.07
Imperial 400N	5	29-30	1.05
Imperial 1000P	5	28-30	1.08

- 13 -

EXAMPLE 4 (varying gel)

The experimental conditions were as follows:

extrusion speed = 9.14m/min
 gel type = 6.0% collagen 6.4% solids
 extrusion calibre = 19mm
 coagulation solution = 21% w/w sodium carbonate

Direct injection of Zesti 10 liquid smoke into gel stream.

Contact time with solution = 40 seconds

The results are given in Table 4.

TABLE 4

Gel usage	Extruder direction
g/min	Tensile Strength (kg)
120	1.08
148	1.28
170	1.44
190	1.64

EXAMPLE 5 (varying extruder disc speed)

The experimental conditions were as follows:

extrusion speed = 15.24m/min
 gel type = 6% collagen 5.4% solids
 extrusion calibre = 19mm
 coagulation solution = 21% w/w sodium carbonate at 40°C

Direct injection of Zesti 10 liquid smoke into gel stream at

5% w/w on gel flow rate of 200g/min.

The results are given in Table 5.

TABLE 5

Disc speed of extruder	Bursting calibre (mm)	Extruder Direction tensile strenth (kg)
60rpm	25-26mm	1.808kg
96rpm	26-27mm	1.959kg
124rpm	26-27mm	2.035kg
184rpm	26mm	1.690kg
240rpm	25-26mm	1.26kg

EXAMPLE 6 (varying extruder disc speed)

The experimental conditions were as follows:

extrusion speed = 41.15m/min
gel type = 4.7% collagen 5.8% solids
extrusion calibre = 19mm
coagulation solution = 21% w/w sodium carbonate at 40°C
gel flow rate = 522g/min.

Direct injection of Zesti 10 liquid smoke into gel stream at 5% w/w.

The results were as follows:

- (a) Extruder disc speed at 265rpm - tensile = 1.866kg
(± 0.254kg)
bursting calibre = 24mm
- (b) Extruder disc speed at 302rpm - tensile = 2.152kg
(± 0.131)
bursting calibre = 24mm.

EXAMPLE 7 (mixed coagulation agents)

The experimental conditions were as follows:

extrusion speed = 15.2m/min
gel flow rate = 199g/min
gel type = 4.7% collagen 5.6% solids
5% by volume at Zesti 10 liquid smoke addition to gel
stream.
coagulation time = 40 seconds
coagulation temperature = 40°C

The results were as follows:

(a) Coagulation solution composition = 21% w/w aqueous sodium carbonate.

Extrusion direction tensile strength = 2.212kg (\pm 0.214kg)

(b) Coagulation solution composition = 18% NaCl and 9.6% Na₂CO₃ by weight.

Extrusion direction tensile strength = 2.055kg (\pm 0.268kg).

CLAIMS

1. A process of producing co-extruded sausage which comprises;
 - co-extruding a substantially uniform layer of collagen gel around an extruded edible product; and
 - chemically coagulating the co-extruded collagen gel using a chemical coagulating agent in the absence of heated air drying, such as to provide around the edible product a coagulated collagen casing of sufficient strength to allow mechanical formation of sausage links.
2. A process according to claim 1 wherein the collagen gel is an acid gel at a pH of 1 to 4.
3. A process according to any preceding claim wherein the collagen gel is at a temperature of 4 to 16°C prior to extrusion.
4. A process according to any preceding claim wherein a further chemical coagulating agent is incorporated into the collagen gel prior to extrusion.
5. A process according to claim 4 wherein the further chemical coagulating agent is liquid smoke.

- 17 -

6. A process according to any preceding claim wherein chemical coagulating agent in the bath is selected from
 - (i) a salt solution such as to dehydrate the collagen casing by osmotic water loss;
 - (ii) an alkali such as to promote dehydration of the collagen casing by pH change; or
 - (iii) a chemical cross-linking agent.
 7. A process according to claim 6 wherein the chemical coagulating agent comprises an aqueous alkali solution of sodium carbonate at a pH of 9 to 13.
 8. A process according to any preceding claim wherein the coagulation time is in the region 5 to 300 seconds.
 9. A process according to any preceding claim wherein the amount of collagen gel co-extruded around the edible product is 3 to 10% of total weight of co-extruded sausage.
 10. A process according to any preceding claim wherein the coagulated collagen casing has a thickness of 10 to 30 microns.
 11. A process according to any preceding claim which includes the further step of mechanically forming into sausage links by crimping or twist-linking.
-

- 18 -

12. A process according to any preceding claim wherein a colouring agent is included or injected in the gel prior to extrusion.

13. A process according to any preceding claim wherein a colouring agent or combination with a cross-linking agent is included or injected in the edible product prior to extrusion.

14. An apparatus for producing co-extruded sausages which comprises;

- means for co-extruding a substantially uniform layer of collagen gel around an extruded edible product; and
- a liquid coagulating bath containing a chemical coagulating agent for chemically coagulating the co-extruded collagen gel in the absence of hot air drying.

15. An apparatus according to claim 14 which further comprises a holding chamber disposed downstream of the coagulating bath for allowing substantial completion of coagulation of the collagen casing.

16. An apparatus according to claim 15 wherein the holding chamber is in the form of a helical flume, down which a treatment liquid may be flowed.

- 19 -

17. An apparatus according to any of claims 14 to 16 which further comprises means for mechanically forming into sausage links by crimping or twist-linking.

18. A co-extruded sausage which comprises an elongate extruded edible product having therearound a coagulated extruded collagen gel casing, the casing incorporating a cross-linking agent and having been chemically coagulated.

1/1




Fig 1

INTERNATIONAL SEARCH REPORT

PCT/GB 92/02381

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 A22C13/00		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	A22C	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
A	Derwent Publications Ltd., London, GB; AN 90-119470 & JP,A,2 069 139 (NIPPON HAM KK) 8 March 1990 cited in the application see abstract ---	1
A	US,A,3 622 353 (N. J. BRADSHAW) 23 November 1971 see claims 1-5; examples 2,3 & GB,A,1 232 801 (UNILEVER LTD.) 19 May 1971 cited in the application ---	1
A	EP,A,0 083 126 (VAESSEN-SCHOEMAKER HOLDING B.V.) 6 July 1983 see claims 1-14 --- -/-	1
<p>¹⁰ Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"A" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
15 APRIL 1993	19. 05. 93	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	PERMENTIER W.A.	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category ^a	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	FR,A,2 226 932 (DEVRO, INC.) 22 November 1974 see claims 1-17 ---	1,4,5
A	US,A,2 988 451 (H. ZAHN) 13 June 1961 see the whole document -----	1

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.

GB 9202381
SA 67871

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 15/04/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-3622353	23-11-71	BE-A- 734585	15-12-69
		DE-A, B, C 1930887	08-01-70
		FR-A- 2011148	27-02-70
		GB-A- 1232801	19-05-71
		NL-A- 6909339	22-12-69
EP-A-0083126	06-07-83	NL-A- 8105898	18-07-83
		AU-B- 537381	21-06-84
		AU-A- 9178582	11-08-83
		CA-A- 1189381	25-06-85
		JP-C- 1558779	16-05-90
		JP-A- 58160324	22-09-83
		JP-B- 63060972	28-11-88
		US-A- 4476072	09-10-84
FR-A-2226932	22-11-74	US-A- 3894158	08-07-75
		AT-B- 351345	25-07-79
		AU-B- 476319	16-09-76
		AU-A- 6760174	09-10-75
		BE-A- 814134	24-10-74
		CA-A- 1023608	03-01-78
		CH-A- 602018	14-07-78
		DE-A- 2419559	21-11-74
		GB-A- 1432271	14-04-76
		JP-A- 50012257	07-02-75
		NL-A- 7405525	28-10-74
US-A-2988451		None	